

DuPont™ Temprion™ EIF X Series

Electrically Insulating Film

Description

DuPont™ Temprion™ EIF X Series is a flexible laminate film comprising an electrically insulating, puncture resistant Kapton® polyimide core coated with a pressure sensitive, thermally conductive adhesive on one or both sides.

Temprion™ EIF features Kapton® MT or Kapton® MT+ polyimide as a carrier to achieve best-in-class thermal performance for an electrically insulating film, where electrically isolating components within a package is critical to operation.

Applications

- · Thermal Interface Material
- · Power Electronics
- · CPU/GPU
- Battery Attachment

Features

- · Low thermal resistance
- · High puncture resistance
- · Minimal application pressure
- UL 94 V-0 flammability rating
- · RoHS Compliance

Table 1 - Typical Properties of DuPont™ Temprion™ EIF X Series Electrically Insulating Film

Property	XA037037D037	XA037037S000	Test Method
Thickness, mil (mm)	4.5 (0.11)	3.0 (0.076)	ASTM D374
Reinforcement Carrier	Kapton® MT+	Kapton® MT+	N/A
Continuous Use Temp, °F (°C)	-4 to +257 (-20 to +125)		N/A
Thermal Conductivity, W/m· K	0.7	0.7	ASTM D5470
Thermal Impedance, °C· in²/W (°C· cm²/W) @ 45 psi (0.3 MPa)	0.24 (1.54)		ASTM D5470
Breakdown Voltage, Vac	7.9	7.9	ASTM D149
Volume Resistivity, Ω· cm	> 1015		ASTM D257
90° Peel Strength @ RT, against smooth AI, 24 hr dwell, lb/in width (N/cm width)	1.1 (1.9)	1.1 (1.9)	ASTM D3330
Flammability	V-0		UL94
RoHS Compliant	Yes		N/A



electronics.dupont.com

For more information on $DuPont^{m}$ Temprion or other DuPont products, please visit our website.

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. It may be subject to revision as new knowledge and experience becomes available. This information is not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for your particular purposes. Since we cannot anticipate all variations in end-use and disposal conditions, DuPont makes no warranties and assumes no liability in connection with any use of this information. It is intended for use by persons having technical skill, at their own discretion and risk. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right.

CAUTION: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, see "DuPont Medical Caution Statement," H-50102-5 and "DuPont Policy Regarding Medical Applications" H-50103-5..

DuPont[™], the DuPont Oval Logo, and all products, unless otherwise noted, denoted with [™], [™] or [®] are trademarks, service marks or registered trademarks of affiliates of DuPont de Nemours, Inc. Copyright © 2019 DuPont de Nemours Inc. All rights reserved.